

TRANSMITTAL LETTER TO THE UNITED STATES DESIGNATED/ELECTED OFFICE (DO/EO/US)		Attorney's Docket Number 202021/140	
International Application No. PCT/KR99/00244	International Filing Date 15 May 1999	Priority Date Claimed 02 December 1998	
Title of Invention: METHODS FOR REFORMING POLYMER SURFACE FOR IMPROVED WETTABILITY			
Applicant (s) for DO/EO/US: LEE, Sang-Young; AHN, Byeong-In; SONG, Heon-Sik and KIM, Myung-Man			
Applicant herewith submits to the DO/EO/US the following items under 35 U.S.C. 371:			
1. <input checked="" type="checkbox"/> This express request to immediately begin national examination procedures (35 U.S.C. 371 (f)).			
2. <input checked="" type="checkbox"/> The U.S. National Fee (35 U.S.C. 371 (c) (1)) and other fees as follows:			
CLAIMS	(1) FOR	(2) NUMBER FILED	(3) NUMBER EXTRA
TOTAL CLAIMS		31 (20)	11
INDEPENDENT CLAIMS		4 (3)	1
MULTIPLE DEPENDENT CLAIM (S) (if applicable)			
BASIC NATIONAL FEE (37) CFR 1.492 (a) (1)-(5)):			
[ ] International preliminary examination fee paid to USPTO (37 CFR 1.482)..... \$			
[ ] No international preliminary examination fee paid to USPTO (37 CFR 1.482) but international search fee ( 37 CFR 1.445 (a) (2)) paid to USPTO (37) CFR 1.445 (a) (2))..... \$			
<input checked="" type="checkbox"/> Neither international preliminary examination fee (37 CFR 1.482) nor international search fee (37 CFR 1.445 (a) (2)) paid to USPTO..... \$970.00			\$ 970.00
[ ] International preliminary examination fee paid to USPTO (37 CFR 1.482) and all claims satis- fied provisions of PCT Article 33 (2) to(4)..... \$			
[ ] For filing with EPO or JPO search report..... \$			\$
Surcharge of \$130.00 for furnishing the National fee or oath or Declaration later than <input checked="" type="checkbox"/> 20 [ ] 30 mos. from the earliest claimed priority date (37 CFR 1.482 (f))			130.00
TOTAL OF ABOVE CALCULATIONS			= 1376.00
Reduction by 1/2 for filing by small entity, if applicable. Affidavit must be filed also. (Note 37 CFR 1.9, 1.27, 1.28.)			
SUBTOTAL			+ 1376.00
Processing fee of \$ for furnishing the English Translation later than [ ] 20 [ ] 30 mos. from the earliest claimed priority date (37 CFR 1.482 (f))			
TOTAL NATIONAL FEE			\$ 1376.00
TOTAL FEES ENCLOSED			\$ 1376.00
a. <input checked="" type="checkbox"/> A check in the amount of \$1376.00 to cover the above fee is enclosed.			
b. [ ] Please change my Deposit Account No. in the amount of \$ to cover the above fees. A duplicate copy of this sheet is enclosed.			
c. <input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. 14-1138. A duplicate copy of this sheet is enclosed.			

09/601310


534 Rec'd PCT/PI 31 JUL 2000


Attorney's Docket Number:  
202021/140

3. A copy of the International Application as filed (35 U.S.C. 371 (c) (2))
  - a. ☐ is transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☐ is not required, as the application was filed in the United States Receiving Office (RO/US).
  - c. ☒ has been transmitted by the International Bureau.
4. ☐ A translation of the International Application into English (35 U.S.C. 371 (c) (2)).
5. Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371 (c) (3)):
  - a. ☐ are transmitted herewith (required only if not transmitted by the International Bureau).
  - b. ☐ have been transmitted by the International Bureau.
  - c. ☐ have not been made; however, the limit for making such amendments has NOT expired.
  - d. ☒ have not been made and will not be made.
6. ☐ A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371 (c) (3)).
7. ☒ A signed oath or declaration of the inventors (35 U.S.C. 371 (c) (4)).
8. ☐ A translation of the Annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371 (c) (5)).
9. ☐ An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
10. ☒ An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
11. ☐ A Preliminary Amendment to the to the claims in the Preliminary Examination Report (copy attached).
12. ☐ Other enclosures include:

13. The above checked items are being transmitted
  - a. ☐ before the 18<sup>th</sup> month publication.
  - b. ☒ after publication and the Article 20 communication but before 20 months from the priority date.
  - c. ☐ by 30 months and a proper demand for International Preliminary Examination was made by the 19<sup>th</sup> month from the earliest claimed priority date.

NAME: GEORGIA CATON  
ADDRESS: NIXON PEABODY LLP  
CLINTON SQUARE, P.O. BOX 31051  
ROCHESTER, NEW YORK 14603

  
SIGNATURE  
REGISTRATION NUMBER: 44,597

  
DATE

## METHODS FOR REFORMING POLYMER SURFACE FOR IMPROVED WETTABILITY

### CROSS REFERENCE TO RELATED APPLICATION

5

This application is based on application No. 98-52484 and No. 99-12643 filed in the Korean Industrial Property Office on December 2, 1998 and April 10, 1999 respectively, the content of which is incorporated hereinto by reference.

10

### BACKGROUND OF THE INVENTION

#### **(a) Field of the Invention**

The present invention relates to a method for reforming surface of polymer, especially to a method for either providing hydrophilicity or increasing hydrophobicity by reforming a surface of polymer material or polymer membrane.

#### **(b) Description of the Related Art**

Polymer membrane is being used widely in various applications such as air purifiers, filter membranes in the water treatment field, electrolysis, separators in batteries, gas exchange membranes, artificial internal organs, beverage purification, enzyme refining, etc.

20 As separators for batteries, these membranes play a role that isolates an anode from a cathode, and thereby preventing short circuits due to the contact between two electric poles, and at the same time passing an electrolyte or ion. Although separator material itself does not contribute to supplying electrical energy, it does affect the performance and safety of battery by its  
25 mechanical characteristics.

There are various required characteristics in a separator of battery that depend on the type of battery and recent varieties of separators have been developed and tried out in secondary, or rechargeable, batteries such as, the

lithium battery that requires different characteristics from separators used in conventional batteries.

Basic characteristics required in separators for battery include the ability to isolate the anode and cathode, low electrical resistance for easy passing of electrolyte or ions, superior wettability with electrolyte, adequate mechanical strength for both assembly and use of the battery, the ability to reduce membrane thickness for high density charging, etc. Separator wettability with the electrolyte is especially influential both directly and indirectly on battery production since after the manufacturing of the jelly roll, the process must await the electrolyte to infiltrate into the separator. Therefore, there is much interest in the battery industry with increasing the electrolyte infiltration speed by inducing hydrophilicity into a hydrophobic separator.

Safety features such as shut down characteristics are especially required because highly active organic solvents are used as electrolyte in secondary batteries. Therefore, a new polymeric separator has been developed because cellulose or non-woven fabric used in the conventional batteries could not satisfy the required characteristics of a separator for the above described secondary battery. There are many separators for this purpose which are generally made of polyolefin resin. Lithium ion batteries in particular could be commercialized by using polyolefin resin, which is the only material which has a low reactivity with highly active organic solvents and a low price.

Methods for manufacturing a ventilating film's precursor film by using polyolefin resin include a wet process where filler or wax and solvent are used to extract low molecular weight material forming pores and a dry process where microscopic pores are formed without using any solvents by stretching at low and at high temperatures. The stretching process related with forming of pores in the dry process frequently employs uni-axial stretching and bi-axial stretching methods. Although there are many processes that can be used theoretically or in laboratories, the only methods for separator manufacturing being used commercially are the above described wet and dry processes.

On the other hand, even though polyolefin based resin is frequently used as separator for lithium ion batteries due to various superior physical properties and economic aspects, this material has a disadvantage in that it has a low wettability with electrolyte because of its inherent hydrophobicity.

5 Therefore, there have been many efforts to counteract the hydrophobicity of polyolefin based membranes.

These include a method for treating membrane surfaces using a surfactant developed by the Hoechst Celanese Company of the U.S.A. and methods for chemically bonding monomer or polymer displaying hydrophilicity to  
10 membranes as taught in United States Patent No. 3,231,530, United States Patent No. 3,853,601, United States Patent No. 3,951,815, United States Patent No. 4,039,440, United States Patent No. 4,340,482, etc.

However, these methods have a lot of problems in that various other unfavorable side chemical reactions cause a molecular weight reduction of  
15 polymer membrane that reduces the durability of the manufactured membrane. Furthermore, the process used with these methods are so complicated that it is not advantageous in economic and mass production aspects, as well as producing a poor working environment due to the use of solvents.

Efforts to reform the surface of polymer membranes include a method  
20 for imparting hydrophilicity by using a corona, or plasma, etc. Methods for grafting a hydrophilic monomer such as acrylic acid and polymers such as polyethylene oxide to the membrane surface are taught in the United States Patent No. 4,346,142, United States Patent No. 5,085,775, and United States Patent No. 5,294,346. Additionally, a method for plasma treating or sputter  
25 etching while at the same time infusing into the membrane surface an oxygen and carbon tetrafluoride ( $\text{CF}_4$ ) gas for alkali secondary battery separators that require hydrophilicity together with hydrophobicity in the battery's discharge characteristics is taught in Japanese Laid-open Patent No. Heisei 8 - 31399. However, the methods using these plasmas have problems in that control of  
30 uniformity is difficult due to plasma's inherent characteristics of high dependence on external environmental factors, broad energy distribution, etc.,

as well as the surface may be damaged mechanically due to other side reactions degrading mechanical properties. In other words, the critical physical properties required in a membrane are difficult to achieve using plasmas.

5 On the other hand, a method for reforming the polymer surface including reducing a contact angle or increasing an adhesion strength of the polymer surface by irradiating it with energized ion particles under vacuum conditions on the polymer surface while at the same time infusing reactive gas into the polymer surface is presented in Korean Laid-open Patent Publication  
10 No. 96 - 37742. This method reports that the contact angle of the polymethylmethacrylate (PMMA) is decreased to 8° among the polymers with reformed surfaces, and the contact angle of polycarbonate can be reduced to such a degree that water drops continue to flow, thus making it impossible to measure a contact angle.

15 However, this method of irradiating ion beams while at the same time infusing a reactive gas is affected by the species of the infused gas selected and the supply of the gas. Furthermore, there are problems in that physical properties of the material, especially the mechanical properties, can deteriorate because the polymer surface can be etched by ancillary ionizations of the  
20 coexisting reactive gas in addition to free radical formations on the polymer surface during the ion beam irradiation. Compared to gases used with ion beam, ionized reactive gases are generally known to deepen the degree of etching on a surface during ionization. These phenomena tend to particularly occur more frequently on the surfaces of membranes which can be damaged  
25 relatively more easily compared to other materials.

### **SUMMARY OF THE INVENTION**

Therefore, it is an object of the present invention considering problems of the conventional technologies to provide a method for reforming the surface of polymer or polymer membrane without deteriorating the mechanical  
30 properties of the polymer or the polymer membrane.

It is other object of the present invention to provide a method for reforming polymer or polymer membrane which has a good working environment and is readily applied in mass production techniques owing to easy surface reforming of polymer or polymer membrane without using any  
5 solvents.

It is another object of the present invention to provide a method for manufacturing polymer membrane which is used as lithium ion secondary battery separator having good wettability.

### **BRIEF DESCRIPTION OF THE DRAWINGS**

10 A more complete appreciation of the invention, and many of the attendant advantages thereof, will be readily apparent as the same becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings, wherein:

FIG. 1 is a scanning electron microscope (SEM) photograph showing  
15 the surface of polyethylene membrane before its surface is treated by irradiation with hydrogen ionic particles of example 1; and

FIG. 2 is a scanning electron microscope (SEM) photograph showing the surface of polyethylene membrane after its surface is treated by irradiation with hydrogen ionic particles of example 1.

### **DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS**

In the following detailed description, only the preferred embodiment of the invention has been shown and described, simply by way of illustration of the best mode contemplated by the inventors of carrying out the invention. As will be realized, the invention is capable of modification in various obvious respects,  
25 all without departing from the invention. Accordingly, the drawings and description are to be regarded as illustrative in nature, and not restrictive.

The present invention as the first method to achieve the above described objects provides a method for reforming surface of polymer membrane wherein energized ion particles are irradiated on surface of polymer  
30 membrane under a vacuum condition.

The above described method is a new method to improve wettability of polymer membrane by striking ion particles on the surface of polymer membrane to change the morphology of the surface, i.e., to cause a physical transformation or roughness change by a size and shape change of the pores of the surface membrane.

Furthermore, the present invention is a method for improving hydrophilicity of polymer film by striking ion particles on the surface of polymer film to change surface roughness.

After polymer membrane or polymer film is put into a vacuum chamber under a high vacuum condition, ion generating gas is infused into an ion gun to produce energized ionic particles, and then the ionic particles are irradiated one side or both sides of the polymer surface to complete the above described method. Power equipment connected to the ion gun is adjusted and particles have available energy of  $10^{-2}$  to  $10^7$  kilo electron volts (keV).

Pore size of the polymer membrane surface irradiated by the ion beam can be changed or the roughness of polymer membrane surface can be altered depending on the types of irradiated ion and the nature of the irradiation. This will result in reduced contacting angles for various solvents.

For general polymer films without any pores, changes to surface roughness reduce the contacting angles of various solvents.

The types of energized ionic particles of the present invention are one or more of types of particles selected from a group comprising of electrons, hydrogen, oxygen, nitrogen, helium, fluorine, neon, argon, krypton, air, and  $N_2O$ .

The irradiation of ion particles of the present invention is preferably performed after the formation of pores in the case of polymer membranes using a wet process, and preferably any time before, in the middle, or after the stretching process forming pores in the case of a dry process. The irradiation time is determined depending on the intended use of the polymer film.

A second method also provides a method for reforming the surface of polymer membrane that includes the steps of:

a) manufacturing a polymer membrane including the activated surface



by inserting a polymer membrane into vacuum chamber and by irradiating energized ionic particles on the surface of polymer membrane under a high vacuum with an ion beam; and

b) manufacturing a polymer membrane treated with a reactive gas reacted on a surface of polymer membrane, including the activated surface of the above step a) by infusing the reactive gas after irradiation by the energized ionic particles.

The above described method can either produce a polymer surface that displays hydrophilicity or increased hydrophobicity, depending on the nature of the reactive gas.

In the above described method, the ion beam irradiation of step a) and the reactive gas infusion of step b) are each separate but performed in series. The reaction with reactive gas after step a) is made in a vacuum chamber and the activated polymer membrane can then be moved into other sealable reaction chamber. One particular example of these is to infuse gas into two reaction chambers which have been connected together while at the same time film is moved from one chamber to the other.

Energized ionic particles of the above described step a) can be irradiated on either one side or both sides of polymer membrane.

The types of ionic particles of the above described step a) can be one or more types of particles or their compounds selected from a group comprising of electrons, hydrogen, oxygen, nitrogen, helium, fluorine, neon, argon, krypton, air, and  $N_2O$ . In fact, any other ion particles can also be used.

The amount of irradiation of energized ion particles in the above described step a) is preferably  $10^5$  to  $10^{20}$  ion/cm<sup>2</sup>, with its energy volume is preferably from  $10^{-2}$  to  $10^7$  keV, and the high vacuum of the above described step a) is preferably  $10^{-2}$  to  $10^{-8}$  torr.

The polymer membrane, including the activated surface, of the above described step a) is the membrane where radicals are formed at the surface of polymer by irradiation of energized ion particles.

The reactive gas of the above described step b) is preferably infused

when pressure in vacuum chamber reaches the range of  $10^{-6}$  to  $10^4$  torr. At

this time, the infusion rate of the reactive gas is preferably 0.5 to 1000 ml/min

and the reactive gases can be used by selecting more than one gases from a group comprising helium, hydrogen, oxygen, nitrogen, air, ammonia, carbon  
5 monoxide, carbon dioxide, carbon tetrafluoride, methane,  $N_2O$ , and their mixtures. In fact, all other gases can also be used.

The material of the polymer membrane which can be applied to the above described method is selected from a polyolefin group comprising polypropylene, high density polyethylene (HDPE), low density polyethylene  
10 (LDPE), and linear low density polyethylene (LLDPE), and is preferably one or more polyolefin blends or polyolefin laminates selected from this polyolefin group.

The precursor films are put into a vacuum chamber having a high vacuum, ion generating gas is infused into ion gun to produce energized ions,  
15 and energized particles are irradiated on one side or both sides of polymer membrane by changing the current of ion beam. This ion beam is irradiated on the polymer membrane in order to form free radicals at the polymer surface. After free radicals are formed by the ion beam irradiation, immediately reactive gas is infused around membrane. Polar or non-polar groups of reactive gas  
20 react with free radical of the polymer membrane surface to provide hydrophilicity or increase hydrophobicity characteristics to the surface of polymer membrane.

By controlling power equipment associated with the above described ion gun, the energy of energized particles is adjusted in the range of 0.01 to 100 keV, the infusion rate of the reactive gas is preferably maintained in the range of  
25 0.5 to 1000 ml/min, and the pressure of the vacuum chamber after the infusion of reactive gas is preferably kept in the range of  $10^{-6}$  to  $10^4$  torr.

The reforming level of the polymer membrane surface of the above described method varies with the irradiation of the ion particles and the variation of the reactive gas parameters including the gas infusion rate and the infusion  
30 amount (e.g., pressure in vacuum chamber).

The above described reactive gas is preferably infused without

interfering with the irradiation of ion particles in the previous step.

Irradiation of a conventional ion beam while simultaneously infusing reactive gas can cause reactive gas ionized by bombardment with ion beam, and the surface of polymer membrane can hence be damaged by ionization of reactive gas, etc. However, the surface of polymer membrane can be reformed without deteriorating its mechanical properties if the reactive gas is infused in after the completion of ion irradiation as in the above described method.

The polymer membrane manufactured in accordance with the above described two methods can be used as a battery separator, and is especially suitable as a separator for lithium ion secondary batteries or alkali secondary batteries.

By using the above described methods, a surface reformed polymer membrane can be produced relatively easily, and this work can be done under a relatively good manufacturing environment as solvents are not used. Additionally, this method is easily adapted to a mass production process.

The above described methods can be applied to all kinds of polymer products in addition to a polymer membrane (such as to polymer films) and have good surface reforming characteristics either because the surface roughness is changed by ion beam irradiation without affecting the matrix of polymer itself or because the reactive gas is reacted on the polymer surface activated by ion beam irradiation resulting in the polymer displaying either hydrophilicity or hydrophobicity.

The present invention is explained in detail by the following examples and comparative examples. However, examples are for illustrating the present invention, and not for limiting the present invention.

In the below described examples and comparative examples, the surface reformed polymer membranes were tested for the following characteristics:

- a) tensile strength and tensile modulus: American Society for Testing and Materials (ASTM) D882,

b) puncture resistance,

c) water absorption speed: Japanese Industrial Standard (JIS) L - 1096,

d) contact angle for electrolyte (mixed solution of ethylene carbonate and dimethyl carbonate).

### EXAMPLE 1

After a polyethylene separator manufactured by a dry process was put into a vacuum chamber maintained under the condition of  $10^{-4}$  torr, hydrogen ion particles ( $H_2^+$ ) were irradiated on both sides of membrane using an ion gun, wherein the energy of the ion beam was 500 eV and the dose of ion irradiation was  $5 \times 10^{14}$  ions/cm<sup>2</sup>. The obtained microporous membrane had a 4.2 second water absorption rate and with a mixture of ethylene carbonate (EC) and dimethyl carbonate (DMC), and showed good wettabilities with electrolyte No.1 having mixing weight % of ethylene carbonate (EC): dimethyl carbonate (DMC) of 4:6, electrolyte No.2 having mixing weight % of 5:5, and electrolyte No.3 having mixing weight % of 6:4. Furthermore, the contact angle could not be measured on electrolyte No.3 showing the greatest polar intensity because the electrolyte solution had permeated into the membrane, which means that the membrane was fully wetted with electrolyte solution.

A scanning electron microscope (SEM) photograph showing the surface of the polyethylene membrane before its surface was irradiated by hydrogen ionic particles is presented in Fig. 1 and a scanning electron microscope (SEM) photograph showing the surface of the polyethylene membrane after its surface was irradiated by hydrogen ionic particles is presented in Fig. 2. From these photographs it is observed that the surface of this polyethylene membrane was coarser after irradiation and that the size of microscopic pores had increased a little.

### EXAMPLE 2

After a polyethylene separator manufactured by a wet process was put into a vacuum vat maintained under the condition of  $10^{-4}$  torr as in example 1, hydrogen ion particles ( $H_2^+$ ) were irradiated on both sides of membrane using an

ion gun, wherein the energy of the ion beam was 400 eV and the amount of ion irradiation was  $1 \times 10^{15}$  ions/cm<sup>2</sup>. The obtained microscopic pore membrane had a 2.5 second water absorption rate. The wettability test on the three electrolytes of electrolyte No. 1, electrolyte No. 2, and electrolyte No. 3 as in example 1 all showed good wettabilities. Furthermore, the contact angle could not be measured on electrolyte No. 3 showing the greatest polar intensity because the electrolyte solution had permeated into the membrane, which means that membrane was fully wetted with electrolyte solution.

#### EXAMPLE 3

After a 3 layer membrane consisting of a top layer of polypropylene, a middle layer of polyethylene, and bottom layer of polypropylene was put into a vacuum chamber maintained under the condition of  $10^{-4}$  torr as in example 1, hydrogen ion particles ( $H_2^+$ ) were irradiated on both sides of membrane using an ion gun, wherein the energy of the ion beam was 900 eV and the dose of ion irradiation was  $1 \times 10^{15}$  ions/cm<sup>2</sup>. The obtained microporous membrane had a 4.8 second water absorption rate. The wettability test on three electrolytes of electrolyte No. 1, electrolyte No. 2, and electrolyte No. 3 as in example 1 all showed good wettabilities. Furthermore, the contact angle could not be measured on electrolyte No. 3 showing the greatest polar intensity because the electrolyte solution had permeated into the membrane, which means that membrane was fully wetted with electrolyte solution.

#### EXAMPLE 4

After a separator made of a blend of polypropylene and polyethylene was put into a vacuum chamber maintained under the condition of  $10^{-4}$  torr as in example 1, hydrogen ion particles ( $H_2^+$ ) were irradiated on both sides of membrane using an ion gun, wherein the energy of the ion beam was 900 eV and the dose of ion irradiation was  $5 \times 10^{14}$  ions/cm<sup>2</sup>. The obtained microporous membrane had a 4.7 second water absorption rate. The wettability test on three electrolytes of electrolyte No. 1, electrolyte No. 2, and electrolyte No. 3 as in example 1 all showed good wettabilities. Furthermore, the contact angle could not be measured on electrolyte No. 3 showing the

greatest polar intensity because the electrolyte solution had permeated into membrane, which means that membrane was fully wetted with electrolyte solution.

#### EXAMPLE 5

5 After low density polyethylene (LDPE) film having a thickness of 25  $\mu\text{m}$  manufactured by a general blowing process was put into a vacuum chamber maintained under the condition of  $10^{-5}$  torr as in example 1, argon ion particles ( $\text{Ar}^+$ ) were irradiated on both sides of membrane using an ion gun, wherein the energy of the ion beam was 2 keV and the dose of ion irradiation was  $1 \times 10^{12}$  ions/cm<sup>2</sup>.  
10

The result of measuring the water contact angle on this obtained film showed a value of less than  $10^\circ$ .

#### COMPARATIVE EXAMPLE 1

The result of measuring the water contact angle on the low density polyethylene (LDPE) film having a thickness of 25  $\mu\text{m}$  manufactured by a  
15 general blowing process as in example 5 showed a value of  $50^\circ$ , a value representing of a substance displaying hydrophobicity physical properties.

#### COMPARATIVE EXAMPLE 2

Polyethylene microporous membrane manufactured by a dry process:

20 Physical properties of a polyethylene microporous membrane manufactured by a dry process, which was manufactured by the Hoechst Celanese Company in the U.S.A., are represented in Table 1.

#### COMPARATIVE EXAMPLE 3

Surface reforming of polyethylene microporous membrane  
25 manufactured by a dry process:

After a polyethylene microporous membrane manufactured by a dry process, which was manufactured by Hoechst Celanese Company in the U.S.A., was put into a vacuum chamber maintained under the condition of  $10^{-5}$  to  $10^{-6}$  torr, hydrogen ion particles ( $\text{H}_2^+$ ) were irradiated on both sides of membrane  
30 using an ion gun while at the same time infusing oxygen as a reactive gas, wherein the energy of ion beam was 0.9 keV, the amount of ion irradiation was

$10^{16}$  ions/cm<sup>2</sup>, and the amount of oxygen gas infusion was 4 ml/min.

The physical properties of the surface reformed microporous membrane are represented in Table 1.

#### EXAMPLE 6

5     Surface reforming of polyethylene microporous membrane  
      manufactured by a dry process:

After a polyethylene microporous membrane manufactured by a general dry process, which was manufactured by Hoechst Celanese Company in the U.S.A., was put into a vacuum chamber maintained under the condition of  $10^{-5}$  to  $10^{-6}$  torr, hydrogen ion particles ( $H_2^+$ ) were irradiated on both sides of membrane using an ion gun forming free radicals on both sides of membrane, wherein the energy of ion beam was 1 keV and the dose of ion irradiation was  $10^{16}$  ions/cm<sup>2</sup>.

Oxygen gas was infused immediately after ion beam irradiation through  
15 a reactive gas infuser at a rate of 200 ml/min until pressure within a vacuum chamber reached atmospheric pressure.

By subsequently infusing the reactive gas, polar groups including oxygen atoms were introduced on the membrane surface. The physical properties of the surface reformed microporous membrane are represented in Table 1.

20                                   COMPARATIVE EXAMPLE 4

Polyethylene microporous membrane manufactured by a wet process:

Physical properties of polyethylene microsporous membrane manufactured with a general wet process by the Tonen Company of Japan, are represented in Table 1.

25                                   EXAMPLE 7

Surface reforming of a polyethylene microporous membrane  
      manufactured by a wet process:

After a polyethylene microporous membrane manufactured with a general wet process by the Tonen Company of Japan was put into a vacuum  
30 vat maintained under the condition of  $10^{-5}$  to  $10^{-6}$  torr, hydrogen ion particles ( $H_2^+$ ) were irradiated on both sides of the membrane using an ion gun forming

free radicals on both sides of the membrane, wherein the energy of ion beam was 0.7 keV and the dose of ion irradiation was  $5 \times 10^{15}$  ions/cm<sup>2</sup>.

Oxygen gas was infused immediately after ion beam irradiation through a reactive gas infuser at a rate of 100 ml/min until pressure within a vacuum chamber reached atmospheric pressure.

By subsequently infusing the reactive gas, polar groups including oxygen atoms were introduced on the membrane surface. The physical properties of the surface reformed microporous membrane are represented in Table 1.

[Table 1]

Classification	Comparative Example 2	Comparative Example 3	Example 6	Comparative Example 4	Example 7
Tensile strength (N/mm; MD/TD)	46/15	34/10	43/14	95/105	90/95
Tensile modulus (N/mm; MD/TD)	720/659	630/570	715/650	1493/789	1385/765
Puncture resistance (g)	280	205	276	410	405
Water absorption Speed (sec)	6.0	3.1	2.6	3.2	1.8
Contact angle on mixed electrolyte having weight % of EC : DMC of 5 : 5 (°)	48	19	12	25	8

As represented in the above described Table 1, it is noticeable that a microporous membrane manufactured by a method for reforming the surface of polymer membrane of the present invention not only shows equal mechanical properties and a faster water absorption rate compared to the microporous membrane which is not treated, but also shows a high surface reforming effect as a hydrophilicity in which the contact angle on the electrolyte is lowered.



Furthermore, surface reforming methods of the present invention, when compared with other methods that greatly deteriorate the mechanical properties of the membrane (such as its tensile strength), display noticeably better membrane surface reforming that imparts hydrophilicity without deteriorating mechanical properties. This is true even when examining comparative examples 3 and 4, which reformed the surface of the polymer membrane by irradiating it with conventional ion particles and simultaneously infusing a reactive gas. This resulted in an increased water absorption rate of the manufactured microporous membrane, and effected the surface hydrophilicity by lowering the contact angle of the electrolyte solution.

The first method of the present invention can improve the wettability of polymer membrane on all kinds of solvents, including water and electrolyte, by irradiating energized particles on the membrane surface of polymer under a vacuum condition without the aid of reactive gas. The wettabilities on various electrolytes are so good that the selection of electrolyte becomes much broader, thus contributing to a large extent to improve assembly and performance when such a treated polymer membrane is used as a separator for lithium secondary battery.

Furthermore, in the second method for reforming the surface of polymer membrane by ion beam irradiation and subsequent reactive gas infusion, this method of the present invention can reform the surface without deteriorating mechanical properties of the polymer membrane while the desired characteristics of the membrane surface reforming (such as hydrophilicity or hydrophobicity) can be obtained by a infused reactive gas.

While the present invention has been described in detail with reference to the preferred embodiments, those skilled in the art will appreciate that various modifications and substitutions can be made thereto without departing from the spirit and scope of the present invention as set forth in the appended claims.

**WHAT IS CLAIMED IS:**

1. A method for reforming the surface of polymer membrane including a step of irradiating energized ion particles on the surface of polymer membrane under vacuum condition.

2. A method in accordance with claim 1, wherein the surface reforming is made on two sides or one side of the membrane.

3. A method in accordance with claim 1, wherein the ionic particles are one or more of types of particles selected from a group comprising electron, hydrogen, oxygen, nitrogen, helium, fluorine, neon, argon, krypton, air, and  $N_2O$ .

4. A method in accordance with claim 1, wherein the energy of the ionic particles is from  $10^{-2}$  to  $10^7$  kilo electron Volts (keV).

5. A method in accordance with claim 1, wherein the dose of the ionic particles is from  $10^3$  to  $10^{20}$  ions/ $cm^2$ .

6. A method for reforming the surface of polymer membrane in accordance with claim 1, wherein the material of the polymer membrane is selected from a polyolefin group comprising polypropylene, high density polyethylene (HDPE), low density polyethylene (LDPE), and linear low density polyethylene (LLDPE).

7. A method for reforming the surface of polymer membrane in accordance with claim 1, wherein the material of polymer membrane is one or more polyolefin blend or polyolefin laminates selected from a polyolefin group comprising polypropylene, high density polyethylene (HDPE), low density polyethylene (LDPE), and linear low density polyethylene (LLDPE).

8. A method in accordance with claim 1, wherein the polymer membrane is a microporous film manufactured either by a dry process where pores are formed by low and high temperature stretching or by a wet process where material of low molecular weight is extracted to form pores.

9. A separator for a lithium ion secondary battery or alkali secondary battery using polymer membrane of which the surface is reformed by a method of claim 1.

10. A method for reforming the surface of polymer including a step of

irradiating energized ion particles on polymer surface under vacuum condition.

11. A method in accordance with claim 10, wherein the surface reforming is made on two sides or one side of polymer film.

12. A method in accordance with claim 10, wherein the ionic particles  
5 are one or more particles selected from a group comprising electron, hydrogen, oxygen, nitrogen, helium, fluorine, neon, argon, krypton, air, and  $N_2O$ .

13. A method in accordance with claim 10, wherein the energy of ionic particles is from  $10^{-2}$  to  $10^7$  keV.

14. A method in accordance with claim 10, wherein the dose of the ionic  
10 particles is from  $10^3$  to  $10^{20}$  ions/cm<sup>2</sup>.

15. A method for reforming the surface of polymer membrane includes the steps of:

- 15 a) manufacturing a polymer membrane including the surface activated by inserting a polymer membrane into a vacuum chamber and by irradiating energized ionic particles on the surface of polymer membrane under a high vacuum; and
- b) manufacturing polymer membrane treated with a reactive gas reacted on the surface of membrane including the activated surface of the above step a) by infusing the reactive gas after the  
20 energized ionic particles of the above step a) have been irradiated.

16. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein surface reforming of polymer membrane provides hydrophilicity or increases hydrophobicity to polymer surface by infusing reactive gas.

25 17. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the reactive gas infusion of step b) is made without interference of the ionic particles.

18. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein ion beam irradiation of the step a) and  
30 reactive gas infusion of step b) are sequentially made.

19. A method for reforming the surface of polymer membrane in

accordance with claim 15, wherein energized ionic particles of step a) are irradiated one side or two sides of polymer membrane.

20. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the ionic particles of step a) are one or more  
5 particles selected from a group comprising electron, hydrogen, oxygen, helium, nitrogen, oxygen, air, fluorine, neon, argon, krypton,  $N_2O$ , and their mixtures.

21. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the dose of irradiation of step a) is from  $10^5$  to  $10^{20}$  ion/cm<sup>2</sup>.

10 22. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the energy of ionic particles of step a) is from  $10^{-2}$  to  $10^7$  keV.

23. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the high vacuum of step b) is  $10^{-2}$  to  $10^{-8}$   
15 torr.

24. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the reactive gas of step b) is infused until the pressure of the vacuum chamber reaches the range of  $10^{-6}$  to  $10^4$  torr.

25. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the infusion rate of the reactive gas of step  
20 b) is 0.5 to 1000 mL/min.

26. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the reactive gases of step b) are one or gases selected from a group comprising helium, hydrogen, oxygen, nitrogen, air,  
25 ammonia, carbon monoxide, carbon dioxide, carbon tetrafluoride, methane,  $N_2O$ , and their mixtures.

27. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the material of polymer membrane of step a) is selected from a polyolefin group comprising polypropylene, high density  
30 polyethylene (HDPE), low density polyethylene (LDPE), and linear low density polyethylene (LLDPE).

28. A method for reforming the surface of polymer membrane in accordance with claim 15, wherein the material of polymer membrane of step a) is one or more polyolefin blends or polyolefin laminates selected from a polyolefin group comprising polypropylene, high density polyethylene (HDPE),  
5 low density polyethylene (LDPE), and linear low density polyethylene (LLDPE).

29. A separator for a battery using the polymer membrane of which the surface is reformed according to the method of claim 15.

30. A separator for battery in accordance with claim 29, wherein the battery is a lithium ion secondary battery or an alkali secondary battery.

10 31. A method for reforming the surface of polymer includes the steps of:

a) manufacturing a polymer including the surface activated by inserting a polymer into a vacuum chamber and by irradiating energized ionic particles on the surface of polymer under high vacuum; and

15 b) manufacturing polymer treated with a reactive gas on the surface of polymer including the activated surface of the above step a) by infusing the reactive gas after the energized ionic particles of the above step a) have been irradiated.

1/1

FIG. 1





FIG. 2



COMBINED DECLARATION FOR PATENT  
APPLICATION AND POWER OF ATTORNEY  
(Includes Reference to PCT International Applications)

ATTORNEY'S DOCKET NUMBER

202021/140

As a below named inventor, I hereby declare that:

My residence, post office address and citizenship are as stated below next to my name.

I believe I am the original, first and sole inventor (if only one name is listed below) or an original, first and joint inventor (if plural names are listed below) of the subject matter which is claimed and for which a patent is sought on the invention entitled:  
"METHODS FOR REFORMING POLYMER SURFACE FOR IMPROVED WETTABILITY"

The specification of which (check only one item below):

☐ is attached hereto.

☐ was filed as U.S. Patent Application Serial No. \_\_\_\_\_ on \_\_\_\_\_ and was amended on \_\_\_\_\_ (if applicable).

☒ was filed as PCT International Application Number PCT/KR99/00244 on May 15, 1999 and was amended under PCT Article 19 on (if applicable).

I hereby state that I have reviewed and understand the contents of the above-identified specifications, including the claims, as amended by any amendment referred to above.

I acknowledge the duty to disclose information which is material to the patentability of this application in accordance with Title 37, Code of Federal Regulations, § 1.56(a).

I hereby claim foreign priority benefits under Title 35, United States Code, § 119 of any foreign application(s) for patent or inventor's certificate or of any PCT international application(s) designating at least one country other than the United States listed below and have also identified below any foreign application(s) for patent or inventor's certificate or any PCT international application(s) designating at least one country other than the United States of America filed by me on the same subject matter having a filing date before that of the application(s) of which priority is claimed:

PRIOR FOREIGN/PCT APPLICATION(S) AND ANY PRIORITY CLAIMS UNDER 35 U.S.C. 119:

COUNTRY (IF PCT, indicate "PCT")	APPLICATION NUMBER	DATE OF FILING (day, month, year)	PRIORITY CLAIMED UNDER 35 USC 119
Republic of Korea	1998-52484	02/12/1998	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
Republic of Korea	1999-12643	10/04/1999	<input checked="" type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO
			<input type="checkbox"/> YES <input type="checkbox"/> NO

COMBINED DECLARATION FOR PATENT  
APPLICATION AND POWER OF ATTORNEY (Continued)  
(Includes Reference to PCT International Applications)

ATTORNEY'S DOCKET NUMBER  
202021/140

I hereby claim the benefit under Title 35, United States Code, § 120 of any United States application(s) or PCT international application(s) designating the United States of America that is/are listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in that/those prior application(s) in the manner provided by the first paragraph of Title 35, United States Code, § 112, I acknowledge the duty to disclose material information as defined in Title 37, Code of Federal Regulations, § 1.56(a) which occurred between the filing date of the prior application(s) and the national or PCT International filing date of this application:

PRIOR U.S. APPLICATIONS OR PCT INTERNATIONAL APPLICATIONS DESIGNATING THE U.S. FOR BENEFIT UNDER 35 U.S.C. 120:

U.S. APPLICATIONS		STATUS (Check One)		
U.S. APPLICATION NUMBER	U.S. FILING DATE	PATENTED	PENDING	ABANDONED
PCT APPLICATIONS DESIGNATING THE U.S.				
PCT APPLICATION NO.	PCT FILING DATE	U.S. SERIAL NUMBERS ASSIGNED (if any)		
PCT/KR99/00244	15 May 1999		X	

POWER OF ATTORNEY: As a named inventor, I hereby appoint the following attorney(s) and/or agent(s) to prosecute this application and transact all business in the Patent and Trademark Office connected therewith. **Michael L. Goldman, Registration No. 30,727; Gunnar G. Leinberg, Registration No. 35,584; Dennis M. Connolly, Registration No. 40,964; Edwin V. Merkel, Registration No. 40,087; Jeffery B. Arnold, Registration No. 39,540; Georgia Caton, Registration No. P-44,597**

Send Correspondence to:

Georgia Caton  
NIXON PEABODY LLP  
Clinton Square, P.O. Box 1051  
Rochester, New York 14603

Direct telephone calls to:  
Georgia Caton  
(716) 263-1672

202	FULL NAME OF INVENTOR	FAMILY NAME <u>Lee</u>	FIRST GIVEN NAME <u>Sang-Young</u>	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY <u>Taejeon-city</u>	STATE/FOREIGN COUNTRY <u>Korea</u> <u>KLX</u>	COUNTRY OF CITIZENSHIP <u>Korea</u>
	POST OFFICE ADDRESS	P.O. ADDRESS <u>LG Chemical Apt. 5-105, 381-42, Doryong-dong, Yuseong-gu</u>	CITY <u>Taejeon-city, Korea</u>	STATE & ZIP CODE/COUNTRY
202	FULL NAME OF INVENTOR	FAMILY NAME <u>Ahn</u>	FIRST GIVEN NAME <u>Byeong-In</u>	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY <u>Taejeon-city</u>	STATE/FOREIGN COUNTRY <u>Korea</u> <u>KLX</u>	COUNTRY OF CITIZENSHIP <u>Korea</u>
	POST OFFICE ADDRESS	P.O. ADDRESS <u>LG Chemical Dormitory 3-406, Doryong-dong 386-2, Yuseong-gu</u>	CITY <u>Taejeon-city, Korea</u>	STATE & ZIP CODE/COUNTRY
303	FULL NAME OF INVENTOR	FAMILY NAME <u>Song</u>	FIRST GIVEN NAME <u>Heon-Sik</u>	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY <u>Taejeon-city</u>	STATE/FOREIGN COUNTRY <u>Korea</u> <u>KAX</u>	COUNTRY OF CITIZENSHIP <u>Korea</u>
	POST OFFICE ADDRESS	P.O. ADDRESS <u>LG Chemical Apt. 9-502, Doryong-dong 381-42, Yuseong-gu</u>	CITY <u>Taejeon-city, Korea</u>	STATE & ZIP CODE/COUNTRY

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

SIGNATURE OF INVENTOR 201 <u>Sang-Young Lee</u>	SIGNATURE OF INVENTOR 202 <u>Byeong In Ahn</u>	SIGNATURE OF INVENTOR 203 <u>Heon-Sik Song</u>
DATE July 13, 2000	DATE July 13, 2000	DATE July 13, 2000



COMBINED DECLARATION FOR PATENT APPLICATION AND POWER OF ATTORNEY (Continued) (Includes Reference to PCT International Applications)				ATTORNEY'S DOCKET NUMBER 202021/140
204	FULL NAME OF INVENTOR	FAMILY NAME <b>Kim</b>	FIRST GIVEN NAME <b>Myung-Man</b>	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY <b>Taejeon-city</b>	STATE/FOREIGN COUNTRY <b>Korea</b> <i>KRX</i>	COUNTRY OF CITIZENSHIP <b>Korea</b>
	POST OFFICE ADDRESS	P.O. ADDRESS <b>Sangroksoo Apt. 108-1408, Mannyun-dong, Seo-gu</b>	CITY <b>Taejeon-city, Korea</b>	STATE & ZIP CODE/COUNTRY
205	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE/FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	P.O. ADDRESS	CITY	STATE & ZIP CODE/COUNTRY
206	FULL NAME OF INVENTOR	FAMILY NAME	FIRST GIVEN NAME	SECOND GIVEN NAME
	RESIDENCE & CITIZENSHIP	CITY	STATE/FOREIGN COUNTRY	COUNTRY OF CITIZENSHIP
	POST OFFICE ADDRESS	P.O. ADDRESS	CITY	STATE & ZIP CODE/COUNTRY
<p>I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under section 1001 of Title 18 of the United States Code, and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.</p>				
SIGNATURE OF INVENTOR 204 <i>Myung-Man Kim</i>		SIGNATURE OF INVENTOR 205		SIGNATURE OF INVENTOR 206
DATE July 13, 2000		DATE		DATE